



**DATA SHEET
DS 058
Rev. 04 dd 10/03/09
INEFIL CROMO 1**

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

CLASSIFICATION

APPROVALS

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.28: ER80S-G	EN ISO 21952-A: G CrMo1Si

DB	TÜV	

ALLOY TYPE

1.25Cr-0.5Mo content to be used for the welding of creep resistant steel.

APPLICATIONS

Low alloy copper-coated solid wire with 1.25% Cr and 0.5% Mo content to be used for the welding of creep resistant steel. Chemical composition of wire conforming to EN ISO specification. It is used in chemical industry and in the ammonia synthesis process, for heat exchangers, boilers, piping and pressure vessels for temperature service up to about 550°C. It will also find applications in the petro-chemical industries, suitable for facing on casting and for casting repairs. To be used under the shield of Ar+CO₂.

MATERIALS TO BE WELDED

ASTM		EN		Others
A387 Gr 11&12	A200 T11	10028-2 13CrMo 4-5	(BS 1501 Gr 620 & 621)	
A182 F11 & F12	A213 T11 & T12	10083-1 25CrMo4	(BS 1502 Gr 620)	
A217 WC6 &WC11	A335 P22	10222-2 14CrMo 4-5	(BS 1503 Gr 620 & 621)	
A234 WP11 & WP12	A335 P11 & P12	(DIN 17210 16MnCr5)	(BS 1504 Gr 621)	
A199 T11		(DIN 13CrMo 4-4)	(BS 3100 Gr B2)	
		(DIN 16CrMo4-4)	(BS 3604 Gr 620/440)	
		(DIN 11CrMo 5-5)	(BS 3059 Gr 620/460)	

WELDING GUIDELINES

Preheat and interpass temperature 150 ÷ 250°C. PWHT at 660 ÷ 700°C for an hour.

TECHNICAL INFORMATION

Gas: Mix Ar- CO₂ (EN 14175)
Welding positions: all positions



WELDING PARAMETERS

Current	DC + Reverse polarity				
Diameter (mm)	0.8	1.0	1.2	1.6	
Volts (V)	16 ÷ 28	17 ÷ 32	18 ÷ 34	19 ÷ 38	
Intensity (A)	60 ÷ 200	80 ÷ 260	100 ÷ 360	130 ÷ 450	



DATA SHEET
DS 058
Rev. 04 dd 10/03/09
INEFIL CROMO 1

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

TYPICAL CHEMICAL COMPOSITION OF WIRE

C %	Mn %	Si %	S %	P %	Cr %	Ni %	Mo %	Cu %	
0.10	1.10	0.60	0.010	0.010	1.20	-	0.50	0.12	

TYPICAL MECHANICAL PROPERTIES

GAS		Yield strength	Tensile strength	Elongation on % 5d	Impact energy (Charpy V)				
		Rs	Rm	A 5d	+ 20°C	0°C	-20°C	-40°C	-60°C
		(MPa)	(MPa)	%	(Joule)	(Joule)	(Joule)	(Joule)	(Joule)
MIX	after PWHT	460	570	23	150	-	-	-	-

PRODUCTS AVAILABLE

Process	Product	Classification AWS	Classification EN
MIG/MAG Solid wire	INEFIL B2 INEFIL B2 L	AWS A 5.28: ER80S-B2 AWS A 5.28: ER70S-B2L	EN 21952-B: G 1CM EN 21952-B: G 1CML
TIG Rods	INETIG B2 INETIG B2 L INETIG CROMO 1	AWS A 5.28: ER80S-B2 AWS A 5.28:ER70S-B2L AWS A 5.28: ER80S-G	EN 21952-B: W 1CM EN 21952-B: W 1CML EN 21952-A: W CrMo1Si
SAW Submerged arc	INESUB EB2 INESUB EB2R	AWS A 5.23: EB2 AWS A 5.23: EB2R	EN 24598-A: S CrMo1 EN 24598-A: S CrMo1
FCAW Cored wire	INETUB B81T5-B2 INETUB M81TG-B2 INETUB R81T1-B2	AWS A 5.29: E81T5-B2 AWS A 5.29: E81TG-B2 AWS A 5.29: E81T1-B2	
SMAW Electrodes	INE B2 INE B2 L	AWS A 5.5: E 8018-B2 AWS A 5.5: E 7018-B2L	EN 3580-A: E CrMo1 EN 3580-A: E CrMo1L